

SUBSTITUTE SPECIFICATION

F-6998

Ser. No. 09/864,778

RUBBER COMPOSITION FOR ADHERING TO STEEL CORDS

BACKGROUND OF THE INVENTION

FIELD OF THE INVENTION

The present invention relates to a rubber composition for adhering to steel
5 cords.

DESCRIPTION OF THE RELATED ART

In order to increase the adhesive force of rubber to steel cords plated with
brass, bronze, or zinc, a cobalt salt of an organic acid has heretofore been exclusively
used. A technique involving blending of the cobalt salt of an organic acid with a
10 rubber composition to promote the formation of an adhesive interface layer onto steel
cords, thus increasing the adhesive force, is known in the art.

In recent years, problems have occurred, such as deterioration in adhesive
force caused by high exothermic heat accompanied by higher operating speeds and
greater horsepower of vehicles, deterioration in adhesive force caused by heat,
15 accompanied by prolonged tire life, or deterioration in adhesive force caused by
moisture and heat over a period of time between manufacture and use, thus requiring
adhesive properties of a higher level.

Although cobalt is excellent in initial adhesion, heat deterioration (heat aging)
causes serious deterioration in adhesive force as described above. Even the use of



SUBSTITUTE SPECIFICATION

F-6998

Ser. No. 09/864,778

cobalt can no longer alone satisfy the needs for the high level of adhesion performance required in recent years. It is probable that cobalt is a strong oxidation promoter, and the action thereof to promote the formation of an adhesive layer causes an increase in the thickness of the adhesive layer during travel to lead to fracture of the rubber layer.

Moreover, cobalt is a rare metal, and countries producing the raw material have had problems with political stability. Accordingly, the use of cobalt is disadvantageous because of high fluctuation in price and an unstable supply of rubber products.

SUMMARY OF THE INVENTION

The invention has been made under the aforesaid circumstances. An object of the invention is to provide a rubber composition for adhering to steel cords, which has excellent heat-resistant adhesion and moist heat-resistant adhesion, as well as excellent initial adhesion and performance at a level comparable to or higher than that in the related art, as to resistance to rubber fracture.

The rubber composition for adhering to steel cords according to embodiments of the present invention demonstrates excellent adhesion to steel cords. The rubber composition is prepared by adding the following components (A) and (B) to 100

SUBSTITUTE SPECIFICATION

F-6998

Ser. No. 09/864,778

weight parts of a rubber component containing natural rubber and/or a diene synthetic rubber.

(A) A mixture of a compound containing nickel, and a compound containing molybdenum; or a compound containing simultaneously nickel, and molybdenum in
5 a metal-converted amount of 0.01 to 10 weight parts.

(B) (b1) 0.2 to 20 weight parts of hexamethylenetetramine or a melamine derivative, and (b2) 0.1 to 10 weight parts of at least one selected from the group consisting of phenol resins, resorcin, resorcin derivatives, and cresol resins.

A composition according to certain embodiments of the present invention is
10 prepared by further adding a compound containing calcium (C) to the foregoing composition.

The composition according to those embodiments of the present invention is prepared by adding the aforesaid compound containing calcium (C) in an amount of 0.1 to 20% in weight ratio to the aforesaid component (A) of the basic composition.

15 Compositions according to still other embodiments of the present invention are prepared by further adding silica (D) to the basic composition or to the calcium-containing composition.

These silica-containing compounds are prepared by adding 1 to 100 weight parts of the aforesaid silica (D) to 100 weight parts of the rubber component of the
20 basic or calcium-containing compositions.

SUBSTITUTE SPECIFICATION

F-6998

Ser. No. 09/864,778

The invention provides a rubber composition for adhering to steel cords which has excellent heat-resistant adhesion and excellent moist heat-resistant adhesion, as well as excellent initial adhesion and performance at a level comparable to or higher than that in the related art, as to resistance to rubber fracture.

5

DETAILED DESCRIPTION OF THE INVENTION

Rubber Components

Examples of rubber components used in the invention include natural rubber and synthetic rubber such as polyisoprene rubber (IR), polybutadiene rubber (BR), styrene-butadiene rubber (SBR), isoprene-isobutylene rubber (IIR), ethylene-
10 propylene-diene rubber (EPDM), and modified rubber thereof. These can be used singly or as a mixture of two or more thereof.

Component (A)

The compound containing nickel, and the compound containing molybdenum are both either an inorganic compound or an organic compound, respectively.

15

Inorganic compounds include nickel oxide, and molybdenum oxide; nickel sulfate, and molybdenum sulfate; nickel phosphate, and molybdenum phosphate; nickel phosphite, and molybdenum phosphite; nickel carbonate, and molybdenum carbonate; and nickel chloride, and molybdenum chloride.

SUBSTITUTE SPECIFICATION

F-6998

Ser. No. 09/864,778

Organic compounds include nickel salts, and molybdenum salts of organic acids; and an organonickel sulfur compound, an organomolybdenum sulfur compound.

5 Preferred nickel salts of organic acids are nickel naphthenate, nickel octylate, nickel propionate, nickel abietate, and nickel acetate in view of excellent adhesion performance.

Preferred molybdenum salts of organic acids are molybdenum naphthenate and/or molybdenum abietate in view of excellent adhesion performance.

10 In component (A), a Ni/Mo ratio (weight converted to metals) is not particularly limited, but preferably is from 2/1 to 20/1. The ratio less than 2/1 may invite problems of being uneconomical (Mo is very costly as compared with Ni) and decreasing hardness (rigidity) of the resulting rubber. Exceeding 20/1 may cause a problem of being unable to acquire sufficient adhesion (Ni cannot compensate for deterioration in adhesion).

15 In these salts of organic acids, it also is possible to blend organic acids. For example, adhesion, particularly moist heat adhesion is preferably improved when component (A) is a mixture of nickel salts of naphthenic acid and octylic acid (naphthenic acid/octylic acid = 1/1 to 1/4 in weight percent) and a molybdenum salt of naphthenic acid.

SUBSTITUTE SPECIFICATION

F-6998

Ser. No. 09/864,778

Naphthenic acid is preferred because the high acid value of, for example, 250 mgKOH/g or more, further improves the adhesion, particularly the heat-resistant adhesion.

Component (B)

5 Component (B) includes combination of the following components (b1) and (b2).

(b1) hexamethylenetetramine or melamine derivatives.

(b2) at least one selected from the group consisting of phenol resins, resorcin, resorcin derivatives, and cresol resins.

10 An example of the melamine derivatives is hexamethoxymethylmelamine.

Examples of the resorcin derivatives include resorcin/ alkylphenol/formalin copolymers and resorcin/formalin reaction products.

Component (B) is used to markedly improve the adhesion, particularly the initial adhesion.

15 Component (C)

Use of compounds containing calcium (C) is preferred because of further improving the adhesion, particularly heat-resistant adhesion.

SUBSTITUTE SPECIFICATION

F-6998

Ser. No. 09/864,778

Examples of compounds containing calcium (C) include calcium borate and calcium neodecanoate, but are not limited to these salts.

Compounds containing calcium (C) are preferably added to component (A) during the preparation thereof on the grounds that an effect of improving the hardness (rigidity) of the resulting rubber can be acquired (When component (C) is
5 added to rubber singly apart from component (A), such effect is not obtained).

Component (D)

Addition of silica (component (D)) further improves the adhesion. Silica used include dry process silica (silicic acid anhydride) and wet process silica (hydrated
10 silicic acid), but are not thus limited.

Carbon Black

Carbon black usable in the invention is generally unlimited, and include carbon blacks classified according to the classification by ASTM D1765, including SAF class having numbers of 100's, ISAF class having numbers of 200's, and HAF
15 class having numbers of 300's which have a high reinforcing action, and particularly include N110, N121, N219, N220, N231, N330, and N339. These can be used singly or as a mixture of two or more thereof.

SUBSTITUTE SPECIFICATION

F-6998

Ser. No. 09/864,778

Blend Ratios of Principal and Other Components

The ratio of component (A) blended is from 0.01 to 10 weight parts (in conversion to metal) to 100 weight parts of the rubber component. The ratio of component (A) less than 0.01 weight part invites a problem of failing to obtain sufficient initial adhesion. Exceeding 10 weight parts results in promoting oxidative deterioration of rubber by metal and decreasing aging resistance of the rubber, and as a result offers a problem of decreasing adhesion after aging. The range is preferably from 0.01 to 5.0 weight parts, and more preferably from 0.01 to 2.0 weight parts (in conversion to metal).

In component (B), the ratio of component (b1) blended is from 0.2 to 20 weight parts to 100 weight parts of the rubber component. The ratio of component (b2) blended is from 0.1 to 10 weight parts to 100 weight parts of the rubber component (The ratio varies depending upon purposes and kinds of resins used and cannot be unconditionally determined). When the ratio of component (b1) blended is less than 0.2 weight part or the ratio of component (b2) is less than 0.1 weight part to 100 weight parts of the rubber component, an effect of improving the adhesion cannot be sufficiently achieved. The ratio of component (b1) blended exceeding 20 weight parts or the ratio of component (b2) exceeding 10 weight parts makes the rubber resinous and fragile. Herein, a preferred range of component (b1) is from 0.5 to 10 weight parts, and that of component (b2) is from 0.5 to 5.0 weight parts.

SUBSTITUTE SPECIFICATION

F-6998

Ser. No. 09/864,778

The ratio of a compound containing calcium (C) blended is from 0.1 to 20 percent in weight ratio to component (A). The ratio of component (c) blended is less than 0.1 weight percent fails to achieve sufficient improvement in heat-resistant adhesion whereas exceeding 20 weight percent makes it difficult to prepare component (A). Herein, a preferred range is from 1 to 10 weight percent.

The ratio of sulfur blended is not particularly limited, and for example, from 1 to 10 weight percent.

EXAMPLES

The invention is illustrated through examples, but is not to be construed as limited by the examples.

Examples and Comparative Examples

Common components as described in the following "table 1" and respective components as described in the following "tables 2 to 4" were blended in ratios as described in the tables. Thereafter, these components were kneaded by use of a Banbury mixer according to a general procedure to prepare rubber compositions. About the resulting rubber compositions, an adhesion test (initial adhesion, heat-resistant adhesion, moist heat-resistant adhesion) and an aging resistance test were carried out and evaluated. The respective procedures of evaluation are as follows:

(1) Adhesion Test

SUBSTITUTE SPECIFICATION

F-6998

Ser. No. 09/864,778

Steel cords plated with brass were arranged at intervals of 12 lengths/25 mm and separated by seating rubber to be evaluated. Two sheets of such rubber were piled and vulcanized at 150°C for 30 min to prepare a sample. Peel force of the sample of 25-mm width was measured by use of an autograph. A covering ratio by the steel cord rubber was evaluated by inspection with the naked eye.

The initial adhesion, heat-resistant adhesion, and moist heat-resistant adhesion were evaluated (Heat-resistant adhesion: undergoing aging in a 160°C oven to evaluate adhesion. Moist heat-resistant adhesion: A sample is placed in an autoclave containing water and subjected to aging in a 105°C oven to evaluate adhesion). Results of measurements were estimated by indexes based on the results of Comparative Example 1 estimated as 100 and described in Tables 2 to 4.

(2) Aging Resistance Test

After aging in a Geer oven (after aging a sample in the 90°C oven), a tensile test was carried out (according to JIS K6253). Retention degrees of breaking extension to the initial value were represented by indexes based on the result of Comparative Example 1 estimated as 100. Resulted are described in Tables 2 to 4.

SUBSTITUTE SPECIFICATION

F-6998

Ser. No. 09/864,778

Table 1

Natural Rubber	100 parts
Carbon Black (HAF)	60 parts
Zinc White	8 parts
Aging Preventive (6C)	2 parts
Insoluble Sulfur	6 parts
Promoter (DZ)	1 part

Table 2

	Comparative Example				
	1	2	3	4	5
Cobalt Stearate	○				
Ni / Mo Sample 1 * ¹					
Ni / Mo Sample 2 * ²					
Ni / Mo Sample 3 * ³		○		○	○
Ni / Mo Sample 4 * ⁴					
Ni / Mo Sample 5 * ⁵					
Ni / Mo Sample 6 * ⁶					
Ni / Mo Sample 7 * ⁷					
Ni / Mo Sample 8 * ⁸					
Amount of the aforesaid Metallic Compound Blended to 100 Parts of Rubber Component (Amount Converted to Metal) (Part)	0.2	0.2		0.005	15
SUMIKANOL 620 (Sumitomo Chemical Co., Ltd.) * ⁹	2		2	2	2
SCILETTU 963L (Mitsui Scitech) * ¹⁰	4		4	4	4
Initial Adhesion					
Peel Force	100	82	76	73	101
Covering Ratio of Rubber	100	100	100	100	100
Heat-Resistant Adhesion (160°C×96h age)					
Peel Force	100	75	88	110	82
Covering Ratio of Rubber	50	50	60	90	60
Moist Heat Adhesion (105°C×96h steam age)					
Peel Force	100	83	105	106	88
Covering Ratio of Rubber	10	10	10	10	5
Aging Resistance (90°C×192h age)					
Degree of Improvement	100	106	110	127	85

SUBSTITUTE SPECIFICATION

F-6998

Ser. No. 09/864,778

Table 3

	Example					
	1	2	3	4	5	6
Cobalt Stearate						
Ni / Mo Sample 1 *¹	○					
Ni / Mo Sample 2 *²		○				
Ni / Mo Sample 3 *³			○			
Ni / Mo Sample 4 *⁴				○		
Ni / Mo Sample 5 *⁵					○	
Ni / Mo Sample 6 *⁶						○
Ni / Mo Sample 7 *⁷						
Ni / Mo Sample 8 *⁸						
Amount of the aforesaid Metallic Compound Blended to 100 Parts of Rubber Component (Amount Converted to Metal) (Part)	0.2	0.2	0.2	0.2	0.2	0.2
SUMIKANOL 620 (Sumitomo Chemical Co., Ltd.) *⁹	2	2	2	2	2	2
SCILETTU 963L (Mitsui Scitech) *¹⁰	4	4	4	4	4	4
Initial Adhesion						
Peel Force	111	114	116	115	111	117
Covering Ratio of Rubber	100	100	100	100	100	100
Heat-Resistant Adhesion (160°C×96h age)						
Peel Force	93	98	100	99	100	96
Covering Ratio of Rubber	80	80	90	80	70	90
Moist Heat-resistant Adhesion (105°C×96h steam age)						
Peel Force	106	104	105	104	106	99
Covering Ratio of Rubber	20	15	10	10	10	20
Aging Resistance (90°C×192h age)						
Degree of Improvement	113	112	111	112	111	100

SUBSTITUTE SPECIFICATION

F-6998

Ser. No. 09/864,778

Table 4

	Example						
	7	8	9	10	11	12	13
Cobalt Stearate							
Ni / Mo Sample 1 * ¹							
Ni / Mo Sample 2 * ²							
Ni / Mo Sample 3 * ³			○	○	○	○	○
Ni / Mo Sample 4 * ⁴							
Ni / Mo Sample 5 * ⁵							
Ni / Mo Sample 6 * ⁶							
Ni / Mo Sample 7 * ⁷	○						
Ni / Mo Sample 8 * ⁸		○					
Amount of the aforesaid Metallic Compound Blended to 100 Parts of Rubber Component (Amount Converted to Metal) (Part)	0.2	0.2	0.2	0.2	0.2	0.2	0.2
SUMIKANOL 620 (Sumitomo Chemical Co., Ltd.) * ⁹	2	2	8			2	2
Resorcin/Formalin Reaction Product PENACOLITE RESIN B19-S (Indospech Co.)				2			
Resorcin (Sumitomo Chemical Co., Ltd.)					2		
SCILETTU 963L (Mitsui Scitech) * ¹²	4	4	10	4	4		4
Hexamethylenetetramine NOXELER H (Ouchi Shinko Kagaku K. K.)						4	
Silica (NIPSEAL AQ, Nippon Silica K. K.)							10
Initial Adhesion							
Peel Force	105	114	116	114	118	114	105
Covering Ratio of Rubber	100	100	100	100	100	100	100
Heat-Resistant Adhesion (160°C×96h age)							
Peel Force	99	104	114	102	98	98	97
Covering Ratio of Rubber	80	70	90	90	90	90	90
Moist Heat-Resistant Adhesion (105°C×96h steam age)							
Peel Force	91	95	127	103	107	103	100
Covering Ratio of Rubber	30	10	30	10	10	15	40
Aging Resistance (90°C×192h age)							
Degree of Improvement	113	107	111	113	109	111	110

SUBSTITUTE SPECIFICATION

F-6998

Ser. No. 09/864,778

- *1) Ni naphthenate/Mo naphthenate (Ni/Mo = 2/1 (mole ratio))
- *2) Ni naphthenate/Mo naphthenate (Ni/Mo = 4/1 (mole ratio))
- *3) Ni naphthenate/Mo naphthenate (Ni/Mo = 6/1 (mole ratio))
- *4) Ni naphthenate/Mo naphthenate (Ni/Mo = 8/1 (mole ratio))
- 5 *5) Ni naphthenate/Mo naphthenate (Ni/Mo = 20/1 (mole ratio))
- *6) Ni naphthenate/Mo naphthenate of high acid value (300 mgKOH/g) (Ni/Mo = 6/1 (mole ratio))
- *7) (Ni octylate + Ni naphthenate [octylic acid: naphthenic acid = 7: 3])/Mo naphthenate (Ni/Mo = 6/1 (mole ratio))
- 10 *8) Ni naphthenate/Mo naphthenate (Ni/Mo = 6/1 (mole ratio)) and Ca borate at a weight ratio of 2%
- *9) Resorcin/alkylphenol/formalin copolymer resin
- *10) Hexamethoxymethylmelamine

SUBSTITUTE SPECIFICATION

F-6998

Ser. No. 09/864,778

ABSTRACT

A rubber composition for adhering to steel cords, having excellent heat-resistant adhesion and moist heat-resistant adhesion, as well as initial adhesion, and performance at a level comparable to or higher than that of the related art in resistance to rubber fracture, is made from components (A) and (B), which are blended to 100 weight parts of rubber components containing natural rubber and/or diene synthetic rubber, wherein component (A) is a mixture of a compound containing nickel and a compound containing molybdenum; or a compound containing nickel and molybdenum simultaneously, in a metal-converted amount of 0.01 to 10 weight parts; and component (B) is a mixture of (b1), which is 0.2 to 20 weight parts of hexamethylenetetramine or a melamine derivative, and (b2), which is 0.1 to 10 weight parts of at least one selected from the group consisting of phenol resins, resorcin, resorcin derivatives, and cresol resins.